

# Technical Data Sheet

## Outlast Rubberized Coating



**DRUMMOND™**  
A LAWSON BRAND



### Overview

Rubberized heavy-duty protective coating seals out dirt, water and salt to prevent rust and corrosion. Outlast is ideal to apply to leaky flashing, gutters and HVAC condensation pans.

### Features/Benefits

- High solids
- High flexibility resists cracking
- Weather-resistant formulations
- Prevents corrosion and rust
- Fast drying
- Single coat coverage
- Multiple colors available
- Aerosol and liquid versions
- Seals out water
- Chemical resistant
- Withstands winter chemicals
- Bonds to most surfaces

### Applications


- Roofs
- Flashing
- Gutters and downspouts
- HVAC
- Automotive and fleet maintenance
- Protective coating
- Sound deadening
- Arboricultural services

### Method of Application

- Prepackaged aerosol
- Bulk liquid for airless sprayers, brush or roller

### Identification

- Aerosol coating



## Sizes

- Black: 20 Fl. Oz. Can Size; 16 Oz. (454g) Net Wt.  
5 Gallon Pails  
31 Fl. Oz. (917ml) Screw-On Container

## Directions for Use

- Aerosol: Surface must be clean and dry. Shake can vigorously for one minute after mixing ball begins to rattle. Shake intermittently during use. Hold can 8" to 12" (20cm to 30.5cm) from surface to be coated. Press spray head to actuate. Move can back and forth releasing button after each stroke. Overlap coats by 50%.
- Bulk: Surface must be clean and dry. Brush-on using a synthetic hair brush or roll-on using a medium nap type roller. Spray using a pot feed type airless sprayer or an appropriate coating gun.
- Dry Times:  
To Touch: 45 to 60 minutes – application temperature 50°F to 90°F (10°C to 32°C)  
To Recoat: 2 hours – application temperature 50°F to 90°F (10°C to 32°C)  
Full Cure: 24 hours – application temperature 50°F to 90°F (10°C to 32°C)
- Coverage (dependent on application):  
Aerosols: Approximately 20 sq. ft. per can  
Liquid Bulk: Approximately 150 sq. ft. per gallon

Note: Item No. DL3160 is specially-packaged as a rubberized coating in a screw-on container/feeder for Lawson Products Outlast Compressed Air Spray Gun, Item No. DD1300.

## Technical Specifications

- Form: Aerosol and liquid bulk
- Color: Various
- Resin System: Various rubber and hydrocarbon resin mixtures
- Solvent System: Solvent mixtures
- Odor: Solvent
- Water Solubility: Nil
- Viscosity: Approximately 1,000 cps @ 70°F (21°C)
- Specific Gravity – Aerosol: 0.93 to 1.100 @ 70°F (21°C)
- Specific Gravity – Liquid Bulk (Color Dependent): 1.000 to 1.200 @ 70°F (21°C)
- Reportable MIR Content – Aerosol (Color Dependent): Less than 1.20 to 1.40
- Reportable VOC Content – Liquid Bulk (Color Dependent), % by Weight: 531 to 550 g/L
- Storage Temperature: Less than 120°F (49°C)
- Application Temperature: 50°F to 90°F (10°C to 32°C)
- Shelf Life: Minimum one year
- HMIS (Aerosol): H:2 F:3 pH:0
- HMIS (Liquid Bulk): H:2 F:3 pH:1